

Chase & Sons® CR300 Separator Tape

CONSTRUCTION Polyester Film

DESCRIPTION Chase & Sons® CR300 is an uncoated corrugated polyester film for use in binder, barrier, and electrical insulation applications.

TECHNICAL DATA

Property	US Customary	Metric	Test Method
Thickness	0.00950"	0.241 mm	ASTM D374
Weight	18.9 lb/csy	102.6 g/m ²	Measured
Yield	5.3 sy/lb 1.75 lbs/mft @ 1" width	9.7 m ² /kg 1.02 kg/km @ 10mm width	Calculated
Tensile Strength	7500 psi	52 MPa	Calculated
Break Strength	70 lbs/1" width	123 N/10mm width	ASTM D882
Elongation	140%	140%	ASTM D882
Density		0.43 g/cc	Calculated

GENERAL PROPERTIES

Color	Clear
Standard Core	3" or 6" Paper
Standard Pad Put-up	3"x12, 15, 18" or 6"x18"

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.