

## Chase & Sons® LG1156 Shielding Tape

**CONSTRUCTION** 0.00200" (51μ) Polyester Film  
0.00035" (9μ) Aluminum Foil



**DESCRIPTION** Chase & Sons® LG1156 is a laminate of polyester film and aluminum foil intended for use as a shielding tape.

### TECHNICAL DATA

Property	US Customary	Metric	Test Method
Thickness	0.00245"	0.062 mm	ASTM D374
Weight	17.5 lb/csy	95.0 g/m <sup>2</sup>	Measured
Yield	5.7 sy/lb 1.62 lbs/mft @ 1" width	10.5 m <sup>2</sup> /kg 0.95 kg/km @ 10mm width	Calculated
Tensile Strength	22500 psi	155 MPa	Calculated
Break Strength	55 lbs/1" width	96 N/10mm width	ASTM D882
Elongation	110%	110%	ASTM D882
Density		1.53 g/cc	Calculated

### GENERAL PROPERTIES

Color	Natural
Standard Core	3" or 6", Paper
Standard Pad Put-up	3"x12, 15, 18" or 6"x18"
Traverse Pad Put-up	3"x12"x3, 6, 12"

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.