

Chase & Sons® LG1200 Shielding Tape

CONSTRUCTION 0.00090" (23μ) Heat Fusible Film
0.00035" (9μ) Aluminum Foil
0.00090" (23μ) Polypropylene Film
0.00035" (9μ) Aluminum Foil



DESCRIPTION Chase & Sons® LG1200 is a laminate of polypropylene film, aluminum foils and an additional heat fusible layer. The end product is intended for use as a shielding tape.

TECHNICAL DATA

Property	US Customary	Metric	Test Method
Thickness	0.00270"	0.069 mm	ASTM D374
Weight	16.7 lb/csy	90.5 g/m ²	Measured
Yield	6.0 sy/lb 1.54 lbs/mft @ 1" width	11.0 m ² /kg 0.90 kg/km @ 10mm width	Calculated
Tensile Strength	13500 psi	93 MPa	Calculated
Break Strength	36 lbs/1" width	63 N/10mm width	ASTM D882
Elongation	60%	60%	ASTM D882
Density		1.32 g/cc	Calculated

GENERAL PROPERTIES

Color	Blue
Core	3" or 6", Paper
Standard Pad Put-up	3"x12, 15, 18" or 6"x18"
Traverse Pad Put-up	3"x12"x3, 6, 12"

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Corporation
295 University Avenue
Westwood, MA 02090
Phone: 800-323-4182
Fax: 781-332-0701
www.chasecorp.com
An ISO 9001:2008
REGISTERED COMPANY