## Chase & Sons® LG1203 Shielding Tape

CONSTRUCTION 0.00200" (51µ) Polyester Film

0.00100" (25µ) Aluminum Foil

 ${\tt DESCRIPTION} \qquad {\tt Chase \& Sons}^{\tt @} \ {\tt LG1203} \ {\tt is \ a \ laminate \ of \ polyester \ film \ and \ aluminum \ foil \ intended}$ 

for use as a shielding tape.

## **TECHNICAL DATA**

Property	US Customary	Metric	Test Method
Thickness	0.00305"	0.077 mm	ASTM D374
Weight	26.0 lb/csy	141.2 g/m²	Measured
Yield	3.8 sy/lb 2.41 lbs/mft @ 1" width	7.1 m²/kg 1.41 kg/km @ 10mm width	Calculated
Tensile Strength	13000 psi	90 MPa	Calculated
Break Strength	40 lbs/1" width	70 N/10mm width	ASTM D882
Elongation	75%	75%	ASTM D882
Density		1.83 g/cc	Calculated

## **GENERAL PROPERTIES**

Color	Blue
Standard Core	3" or 6", Paper
Standard Pad Put-up	3"x12, 15, 18" or 6"x18"
Traverse Pad Put-up	3"x12"x3, 6, 12"

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Corporation 295 University Avenue Westwood, MA 02090

Phone: 800-323-4182 Fax: 781-332-0701 www.chasecorp.com

An ISO 9001:2008 REGISTERED COMPANY