

Chase & Sons® LG926SL Shielding Tape

CONSTRUCTION 0.00035" (9µ) Aluminum Foil

0.00100" (25μ) Polyester Film 0.00035" (9μ) Aluminum Foil

 ${\tt DESCRIPTION} \qquad {\tt Chase \& Sons}^{\circledR} \ {\tt LG926SL} \ is \ a \ tri-laminate \ of \ polyester \ film \ and \ aluminum \ foils \ with$

a dry lubricant coating on one foil side intended for use as a shielding tape in

applications of high speed folding and wrapping.

TECHNICAL DATA

Property	US Customary	Metric	Test Method
Thickness	0.00170"	0.043 mm	ASTM D374
Weight	15.2 lb/csy	82.5 g/m²	Measured
Yield	6.6 sy/lb 1.41 lbs/mft @ 1" width	12.1 m²/kg 0.82 kg/km @ 10mm width	Calculated
Tensile Strength	20500 psi	141 MPa	Calculated
Break Strength	35 lbs/1" width	61 N/10mm width	ASTM D882
Elongation	109%	109%	ASTM D882
Density		1.91 g/cc	Calculated

GENERAL PROPERTIES

Color	Natural
Standard Core	3" or 6", Paper
Standard Pad Put-up	3"x12, 15, 18" or 6"x18"
Traverse Pad Put-up	3"x12"x3, 6, 12"

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Corporation 295 University Avenue Westwood, MA 02090

Phone: 800-323-4182 Fax: 781-332-0701 www.chasecorp.com

An ISO 9001:2008 REGISTERED COMPANY