

## Chase & Sons® S384D Heat and Flame Barrier Tape

**CONSTRUCTION**      Glass Fabric  
Neoprene Coating

**DESCRIPTION**      Chase & Sons® S384D is a flame retardant, pinhole free, cured neoprene impregnated glass fabric tape. Suitable for a wide variety of applications where flexible, non-conductive cured tape is required.

### TECHNICAL DATA

Property	US Customary	Metric	Test Method
Thickness	0.006 in	0.152 mm	ASTM D374
Weight	35.5 lb/csy	192.8 gm/m <sup>2</sup>	Measured
Yield	2.8 sy/lb 3.29 lbs/mft @ 1" width	5.2 m <sup>2</sup> /kg 1.93 kg/km @ 10mm width	Calculated
Break Strength	150 lbs/1" width	263 N/10mm width	Calculated
Tensile	25000 psi	173 MPa	ASTM D882
Limiting Oxygen Index (LOI)	29.5	29.5	ASTM D2863

### GENERAL PROPERTIES

Color	Black
Surface	Dry, dusted
Standard Core	3" or 6" Paper

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.