



## NEPTAPE® Data Sheet

### Coated / Fusible Shielding Tapes NEPTAPE® 1001E

**Construction:** 0.00035" (9μ) aluminum foil  
0.00048" (12μ) polyester film  
0.00020" (6μ) fusible olefin coating

**Description:** Thin gauge shielding laminate that bonds to polyethylene or itself at the overlap.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.001 inches	25 microns	ASTM D374
Yield	107.7 ft <sup>2</sup> /lb 0.77 lbs/mft @ 1" wide	22.06 m <sup>2</sup> /kg 0.45 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	17,300 psi	110 MPa	Calculated
Break Strength	16 lbs/in width	28 N/10mm width	ASTM D882
Elongation at Break	75%	75%	ASTM D882
Dielectric Strength of Film	2.8 kV	2.8 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.62 g/cm <sup>3</sup>	Calculated
Max. Continuous Operating Temperature	175°F	80°C	Supplier Data
Sealing Temperature	210-240°F	100-115°C	NEPTCO TM-008
Electrical Resistance	42 Ω/mft @ 1" wide	350 Ω/km @ 10mm wide	Supplier Data
Colors	Blue on fusible side, other colors available upon request		
Splice Type	#53, max. 5/pad for < 22" OD or max. 6/pad for > 22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

**NEPTCO, Incorporated**  
Box 2323, 30 Hamlet Street  
Pawtucket, RI 02861-0323 USA  
TEL: 401-722-5500  
FAX: 401-722-6378