

Coated / Fusible Shielding Tapes

NEPTAPE® 1001F7

Construction: 0.00035" (9μ) aluminum foil
0.00048" (12μ) polyester film
0.00070" (18μ) EAA film

Description: Fusible three ply shielding tape which bonds to a polyethylene core and to itself at overlap.

| Typical Properties | US Customary | Metric | Test Method |
|---------------------------------------|---|--|------------------|
| Thickness | 0.0017 inches | 43 microns | ASTM D374 |
| Yield | 79.0 ft ² /lb 1.05 lbs/mft @ 1" wide | 16.18 m ² /kg 0.62 kg/km @ 10mm wide | NEPTCO TM-002 |
| Tensile Strength | 11,800 psi | 81 MPa | Calculated |
| Break Strength | 20 lbs/in width | 35 N/10mm width | ASTM D882 |
| Elongation at Break | 100% | 100% | ASTM D882 |
| Dielectric Strength of Film | 2.8 kV | 2.8 kV | Supplier Data |
| Dielectric Constant of Film | 3.0 (dimensionless) | 3.0 (dimensionless) | Supplier Data |
| Density | NA | 1.52 g/cm ³ | Calculated |
| Max. Continuous Operating Temperature | 175°F | 80°C | Supplier Data |
| Sealing Temperature | 210-240°F | 100-115°F | NEPTCO TM-008 |
| Electrical Resistance | 42 Ω/mft @ 1" wide | 350 Ω/km @ 10km wide | Supplier Data |
| Colors | Blue | | |
| Splice Type | #53, max. 5/pad for < 22" OD or max. 6/pad for > 22" OD Max. 1/1000' for traverse packages | | |
| Standard Pad Put-ups | Core ID - 3" or 6" Pad OD - 12" or 18" | | |
| Standard Traverse Put-ups | 3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3" | | |

ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.



The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

NEPTCO, Incorporated
Box 2323, 30 Hamlet Street
Pawtucket, RI 02861-0323 USA
TEL: 401-722-5500
FAX: 401-722-6378
www.neptco.com