



NEPTAPE® Data Sheet

Coated / Fusible Shielding Tapes NEPTAPE® 5325F

Construction: 0.00100" (25μ) EAA film
0.00048" (12μ) polyester film
0.00150" (38μ) aluminum foil

Description: Fusible shielding tape typically used for ANSI/IEEE 802.5 network cables Type I & II.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0031 inches	79 microns	ASTM D374
Yield	33.0 ft ² /lb 2.53 lbs/mft @ 1" wide	6.76 m ² /kg 1.48 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	8,400 psi	58 MPa	Calculated
Break Strength	26 lbs/in width	46 N/10mm width	ASTM D882
Elongation at Break	19%	19%	ASTM D882
Dielectric Strength of Film	2.8 kV	2.8 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.88 g/cm ³	Calculated
Max. Continuous Operating Temperature	175°F	80°C	Supplier Data
Sealing Temperature	210-240°F	100-115°C	NEPTCO TM-008
Electrical Resistance	12 Ω/mft @ 1" wide	100 Ω/km @ 10mm wide	Supplier Data
Colors	Blue/Red/Orange - Other colors available upon request.		
Splice Type	#37, max. 5/pad for < 22" OD or 6/pad for > 22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.