



NEPTAPE® Data Sheet

Coated / Fusible Shielding Tapes NEPTAPE® 7001

Construction: 0.00035" (9μ) aluminum foil
0.00048" (12μ) polyester film
release coat

Description: Two ply tape with release coating which prevents bonding to over-extruded PVC jackets.
Typically shields jacketed flat cable.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0009 inches	23 microns	ASTM D374
Yield	112 ft ² /lb 0.74 lbs/mft @ 1" wide	22.9 m ² /kg 0.44 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	19,100 psi	132 MPa	Calculated
Break Strength	17 lbs/in width	30 N/10mm width	ASTM D882
Elongation at Break	98%	98%	ASTM D882
Dielectric Strength of Film	2.8 kV	2.8 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.91 g/cm ³	Calculated
Electrical Resistance	42 Ω/mft @ 1"wide	350 Ω/km @ 10mm wide	Supplier Data
Colors	Natural (Clear), Blue Red, Green, Gold		
Splice Type	#53, max. 5/pad for < 22" OD or 6/pad for > 22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 11" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.