



## NEPTAPE® Data Sheet

### Core Wrap / Separator Tapes NEPTAPE® M150C

**Construction:** 0.00142" (36 $\mu$ ) polyester film  
0.00010" (3 $\mu$ ) colored coating

**Description:** Colored, slit film which wraps and binds conductors, separating them from cable fillers. Color coating provides easy verification of tape removal at termination in typical applications such as power cables.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0016 inches	41 microns	ASTM D374
Yield	91.7 ft <sup>2</sup> /lb 0.91 lbs/mft @ 1" wide	18.8 m <sup>2</sup> /kg 0.53 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	24,900 psi	172 MPa	Calculated
Break Strength	39 lbs/in width	69 N/10mm width	ASTM D882
Elongation at Break	148%	148%	ASTM D882
Dielectric Strength of Film	5.5 kV	5.5 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.30 g/cm <sup>3</sup>	Calculated
Max. Continuous Operating Temperature	220°F	105°C	Supplier Data
Sealing Temperature	NA	NA	NEPTCO TM-008
Splice Type	#5, max. 6/pad or max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

\*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

**NEPTCO, Incorporated**  
Box 2323, 30 Hamlet Street  
Pawtucket, RI 02861-0323 USA  
TEL: 401-722-5500  
FAX: 401-722-6378