



## NEPTAPE® Data Sheet

### Core Wrap / Separator Tapes NEPTAPE® M200L

**Construction:** 0.00092" (23μ) polyester film  
0.00092" (23μ) polyester film

**Description:** Colored, slit film which wraps and binds conductors, separating them from cable fillers. Laminated color provides encapsulated, abrasion resistant verification of tape removal at termination in typical applications such as power cable.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0019 inches	48 microns	ASTM D374
Yield	72.0 ft <sup>2</sup> /lb 1.16 lbs/mft @ 1" wide	14.7 m <sup>2</sup> /kg 0.68 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	26,800 psi	185 MPa	Calculated
Break Strength	52 lbs/in width	91 N/10mm width	ASTM D882
Elongation at Break	133%	133%	ASTM D882
Dielectric Strength of Film	NA	NA	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.40 g/cm <sup>3</sup>	Calculated
Max. Continuous Operating Temperature	220°F	105°C	Supplier Data
Sealing Temperature	NA	NA	NEPTCO TM-008
Splice Type	#5, max. 6/pad or max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

\*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

**NEPTCO, Incorporated**  
Box 2323, 30 Hamlet Street  
Pawtucket, RI 02861-0323 USA  
TEL: 401-722-5500  
FAX: 401-722-6378