



NEPTAPE® Data Sheet

Core Wrap / Separator Tapes NEPTAPE® M400

Construction: 0.00400" (102μ) polyester film

Description: Slit film which wraps and binds conductors, separating them from cable fillers and jacketing materials. Typically used in multiconductor cables.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0040 inches	102 microns	ASTM D374
Yield	34.5 ft ² /lb 2.42 lbs/mft @ 1" wide	7.1 m ² /kg 1.42 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	25,300 psi	170 MPa	Calculated
Break Strength	101 lbs/in width	177 N/10mm width	ASTM D882
Elongation at Break	219%	219%	ASTM D882
Dielectric Strength of Film	12.3 kV	12.3 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.40 g/cm ³	Calculated
Max. Continuous Operating Temperature	220°F	105°C	Supplier Data
Sealing Temperature	NA	NA	NEPTCO TM-008
Splice Type	#5, max. 6/pad or max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.