



NEPTAPE® Data Sheet

Core Wrap / Separator Tapes NEPTAPE® M50E

Construction: 0.00048" (12 μ) polyester film
0.00020" (5 μ) heat seal coating

Description: High yield, heat sealable, slit film which wraps and binds conductors, separating them from cable fillers. Specifically designed to bond to olefin substrates.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0007 inches	18 microns	ASTM D374
Yield	246.9 ft ² /lb 0.34 lbs/mft @ 1" wide	50.57 m ² /kg 0.20 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	21,400 psi	148 MPa	Calculated
Break Strength	15 lbs/in width	26 N/10mm width	ASTM D882
Elongation at Break	97%	97%	ASTM D882
Dielectric Strength of Film	2.8 kV	2.8 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.11 g/cm ³	Calculated
Max. Continuous Operating Temperature	175°F	80°C	Supplier Data
Sealing Temperature	210-240°F	100-115°C	NEPTCO TM-008
Splice Type	#4, max. 6/pad or max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.