



NEPTAPE® Data Sheet

Core Wrap / Separator Tapes NEPTAPE® MT050C

Construction: 0.00048" (12μ) polyester film
0.00050" (13μ) heat seal coating

Description: High yield, heat sealable, slit film which wraps and binds conductors, separating them from cable fillers. Heat sealable to polyester, aluminum and itself.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0010 inches	25 microns	ASTM D374
Yield	194.2 ft ² /lb 0.43 lbs/mft @ 1" wide	39.8 m ² /kg 0.25 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	14,800 psi	102 MPa	Calculated
Break Strength	15 lbs/in width	26 N/10mm width	ASTM D882
Elongation at Break	111%	111%	ASTM D882
Dielectric Strength of Film	2.8 kV	2.8 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.23 g/cm ³	Calculated
Max. Continuous Operating Temperature	175°F	80°C	Supplier Data
Sealing Temperature	300-320°F	150-160°C	NEPTCO TM-008
Splice Type	#6, max. 6/pad or max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.