



NEPTAPE® Data Sheet

SHIELDING TAPE - Standard Film/Foil Laminates NEPTAPE® 1069

Construction: 0.00092" (23μ) polyester film
0.00035" (9μ) aluminum foil

Description: General purpose, white shielding laminate which typically performs as an overall or individual pair shield in electronic cable.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0014 inches	36 microns	ASTM D374
Yield	82.5 ft ² /lb 1.01 lbs/mft @ 1" wide	16.9 m ² /kg 0.59 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	19,900 psi	137 MPa	Calculated
Break Strength	27 lbs/in width	48 N/10mm width	ASTM D882
Elongation at Break	118%	118%	ASTM D882
Dielectric Strength of Film	4.0 kV	4.0 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.67 g/cm ³	Calculated
Electrical Resistance	42 Ω/mft @ 1" wide	350 Ω/km @ 10mm wide	Supplier Data
Colors	Blue		
Splice Type	#53, max. 5/pad for < 22" OD or 6/pad for > 22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.