



NEPTAPE® Preliminary Data Sheet

SHIELDING TAPE - Standard Film/Foil Laminates NEPTAPE® 1264

Construction: 0.00092" (23μ) polyester film
0.00140" (36μ) 1.0 ounce electrodeposited copper foil

Description: High strength copper laminate typically used as a salt corrosion resistant shield in military cable.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0024 inches	61 microns	ASTM D374
Yield	14.4 ft ² /lb 5.79 lbs/mft @ 1" wide	2.90 m ² /kg 3.39 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	37,300 psi	257 MPa	Calculated
Break Strength	90 lbs/in width	157 N/10mm width	ASTM D882
Elongation at Break	21%	21%	ASTM D882
Dielectric Strength of Film	4.0 kV	4.0 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	5.57 g/cm ³	Calculated
Electrical Resistance	7 Ω/mft @ 1" wide	58 Ω/km @ 10mm wide	Supplier Data
Colors	Natural (Copper)		
Splice Type	#13, max. 5/pad for < 22" OD or 6/pad for > 22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific Test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.