



## NEPTAPE® Data Sheet

# SHIELDING TAPE - Standard Film/Foil Laminates NEPTAPE® FF7010

**Construction:** 0.00048" (12μ) polyester film  
0.00100" (25μ) aluminum foil  
0.00048" (12μ) polyester film

**Description:** Polyester/aluminum/polyester laminate, used for shielding or as a vapor barrier in cable applications.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0022 inches	56 microns	ASTM D374
Yield	45.29 ft <sup>2</sup> /lb 1.84 lbs/mft @ 1" wide	9.28 m <sup>2</sup> /kg 1.08 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	17,300 psi	119 MPa	Calculated
Break Strength	38 lbs/in width	67 N/10mm width	ASTM D882
Elongation at Break	86%	86%	ASTM D882
Dielectric Strength of Film	NA	NA	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.93 g/cm <sup>3</sup>	Calculated
Electrical Resistance	15 Ω/mft @ 1" wide	125 Ω/km @ 10mm wide	Supplier Data
Colors	Natural (Clear) - Other colors available upon request.		
Splice Type	#40, max. 5/pad for < 22" OD or 6/pad for > 22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

\*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.