



## NEPTAPE® Data Sheet

# SHIELDING TAPE - Standard Foil/Film/Foil Laminates NEPTAPE® 1122

**Construction:** 0.00200" (51 $\mu$ ) aluminum foil  
0.00092" (23 $\mu$ ) polyester film  
0.00035" (9 $\mu$ ) aluminum foil

**Description:** Three ply shielding tape providing contact between the shielding tape and the drain wire, and simplified peel back for connectors. Used in IEEE 802.3 thin LAN coax cables.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0035 inches	89 microns	ASTM D374
Yield	24.5 ft <sup>2</sup> /lb 3.40 lbs/mft @ 1" wide	5.0 m <sup>2</sup> /kg 1.99 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	13,300 psi	92 MPa	Calculated
Break Strength	46 lbs/in width	81 N/10mm width	ASTM D882
Elongation at Break	19%	19%	ASTM D882
Dielectric Strength of Film	4.0 kV	4.0 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	2.24 g/cm <sup>3</sup>	Calculated
Electrical Resistance	7 $\Omega$ /mft @ 1" wide	58 $\Omega$ /km @ 10mm wide	Supplier Data
Colors	Natural/Clear		
Splice Type	#37, max. 5/pad for < 22" OD or 6/pad for > 22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		

\*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

**NEPTCO, Incorporated**  
Box 2323, 30 Hamlet Street  
Pawtucket, RI 02861-0323 USA  
TEL: 401-722-5500  
FAX: 401-722-6378