



Low Smoke Shielding Tapes

NEPTAPE® FIREFITE® LSP48A Revised / Preliminary

Construction: 0.00035 " (9 μ) Aluminum
0.00055" (14 μ) Polyolefin Film
0.00035" (9 μ) Aluminum
0.00015" (4 μ) EAA Fusible Coating

Description: Three ply bondable low smoke tape used for plenum coaxial applications.

TYPICAL PROPERTIES	English		Metric		Test Method
Overall Thickness	0.0017	inches	43	microns	ASTM D374
Yield	70.3	sq ft/lb	14.40	sq m/kg	NEPTCO
	1.19	lbs/mft @ 1" wide	0.69	kg/km @ 10 mm wide	TM-002
Tensile Strength	9,100	psi	63	MPa	Calculated
Break Strength	15.54	lbs/in. width	27	N/10mm width	ASTM D882
Elongation at Product Break	20	%	20	%	ASTM D882
Dielectric Strength (Film)			0.8	kV	Supplier Data
Dielectric Constant (Film)	2.0	(dimensionless)	2.0	(dimensionless)	Supplier Data
Density			1.61	g/cc	Calculated
Electrical Resistance	21	Ω /mft @ 1" wide	175	Ω /km @ 10 mm wide	Supplier Data
Colors					
Splice Type	#53, max. 5/pad for < 22" OD or max. 6/pad for >22" OD				
	Max. 1/1000' for traverse packages				
Standard Pad Put-ups	Core ID - 3" or 6"				
	Pad OD - 12" or 18"				
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material				
	3" x 11" x 3"				



Please review supplier information before handling and / or using this product.

NEPTCO only warrants that its products will work in a manner consistent with the capabilities described. This information corresponds to our current knowledge of the subject and it is not intended to substitute for any testing you may need to conduct to determine suitability of our product for your particular purpose. Except for the express warranty and limited remedies described herein, NEPTCO DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. The Buyer's remedies under the limited warranty stated above shall be limited to a return of the purchase price of the product. NEPTCO and its authorized agents shall not be liable for any other damages including consequential damages, incurred in connection with the use or performance of the product. This warranty shall be void if the product has been tampered with or improperly used. NEPTCO reserves the right to improve, enhance, and / or modify the features and specifications of these products.