



## NEPTAPE® Data Sheet

# Marker Identification Tapes

## NEPTAPE® M18LCS

**Construction:** 0.00048" (12 $\mu$ ) coextruded polyester film  
0.00092" (23 $\mu$ ) white polyester film

**Description:** 1/8" (3.2 mm) wide identification tape printed with legend, sequential footage markings, and white polyester film on one side. Print is laminated between two film layers that protect it from exposure to water, abrasion, lubricating oils, and filling compounds.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0014 inches	36 microns	ASTM D374
Yield	99.6 ft <sup>2</sup> /lb. 0.84 lbs/mft @ 1" wide	20.4 m <sup>2</sup> /kg 0.49 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	20,000 psi	138 MPa	Calculated
Break Strength	28 lbs/in width	49 N/10mm width	ASTM D882
Elongation at Break	110%	110%	ASTM D882
Dielectric Strength of Film	NA	NA	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.28 g/cm <sup>3</sup>	Calculated
Max. Continuous Operating Temperature	220°F	105°C	Supplier Data
Sealing Temperature	NA	NA	NEPTCO TM-008
Colors	White		
Splice Type	#24, max. 1/1000' for traverse packages		
Standard Pad Put-ups	NA		
Standard Traverse Put-ups	2" ID x 12,000 ft x 6" T - w/ 7/16" arbor hole		

\*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

**NEPTCO, Incorporated**  
Box 2323, 30 Hamlet Street  
Pawtucket, RI 02861-0323 USA  
TEL: 401-722-5500  
FAX: 401-722-6378