

NEPTAPE® LSP48 Revised/Preliminary Low Smoke Shielding Tape

CONSTRUCTION .00035" (9μ) Aluminum Foil
 .00055" (14μ) Polyolefin Film
 .00035" (9μ) Aluminum Foil

DESCRIPTION Three ply, low smoke tape used for plenum coaxial applications.

TECHNICAL DATA

Property	US Customary	Metric	Test Method
Thickness	0.0016 inches	41 Microns	ASTM D374
Yield	73 sq ft/lb. 1.14 lbs/mft @ 1" wide	14.95 sq m/kg 0.67 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	9,100 psi	63 MPa	Calculated
Break Strength	14.5 lbs./inch width	25 N/10mm width	ASTM D882
Elongation at Break	15%	15%	ASTM D882
Dielectric Strength of Film		0.8 kV	Supplier Data
Dielectric Constant of Film	2.0 (Dimensionless)	2.0 (Dimensionless)	Supplier Data
Density		1.65 g/cc	Calculated
Electrical Resistance	21 Ω/mft@ 1" Wide	175 Ω/km @ 10mm Wide	Supplier Data
Colors	Natural / Clear		
Splice Type	#53, max. 5/pad for < 22" OD or max. 6/pad for > 22" OD Max. 1/1000 ¹ for traverse packages.		
Standard Pad Put-Ups	Core ID – 3" or 6" Pad OD – 12" or 18"		
Standard Traverse Put-Ups	3" x 5.75" x 3.5" - Narrow Slit Material 3" x 11" x 3"		

*ASTM test methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. No warranty is expressed or implied by this information. Specification data can be provided upon request.

Chase Corporation
 295 University Avenue
 Westwood, MA 02090
 Phone: 800-323-4182
 Fax: 781-332-0701
 www.chasecorp.com
 An ISO 9001:2008
 REGISTERED COMPANY