

## Shielding Tapes - Standard Foil / Film / Foil Laminates

### P26 Preliminary

**Construction:** 0.00035" (9  $\mu$ ) aluminum foil  
 0.00090" (23  $\mu$ ) polypropylene film  
 0.00035" (9  $\mu$ ) aluminum foil

**Description:** Three ply shielding tape frequently used as the non-fusible outer shield in quad-shielded CATV cable.

TYPICAL PROPERTIES	English	Metric	Test Method
Overall Thickness	0.0018 inches	46 microns	ASTM D374
Yield	65 sq ft/lb	13.31 sq m/kg	NEPTCO
	1.28 lbs/mft @ 1" wide	0.75 kg/km @ 10 mm wide	TM-002
Tensile Strength	14,400 psi	99 MPa	Calculated
Break Strength	26 lbs/in. width	46 N/10mm width	ASTM D882
Elongation at Product Break	87 %	87 %	ASTM D882
Dielectric Strength (Film)		3.8 kV	Supplier Data
Dielectric Constant (Film)		2.0	Supplier Data
Density		1.63 g/cc	Calculated
Electrical Resistance	21 $\Omega$ /mft @ 1" wide	175 $\Omega$ /km @ 10 mm wide	Supplier Data
Colors	Natural/Clear		
Splice Type	#15, max. 5/pad for < 22" OD or max. 6/pad for >22" OD Max. 1/1000' for traverse packages		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 12" or 18"		
Standard Traverse Put-ups	3" x 5.75" x 3.5" - narrow slit material 3" x 11" x 3"		



Please review supplier information before handling and / or using this product.

NEPTCO only warrants that its products will work in a manner consistent with the capabilities described. This information corresponds to our current knowledge of the subject and it is not intended to substitute for any testing you may need to conduct to determine suitability of our product for your particular purpose. Except for the express warranty and limited remedies described herein, NEPTCO DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. The Buyer's remedies under the limited warranty stated above shall be limited to a return of the purchase price of the product. NEPTCO and its authorized agents shall not be liable for any other damages including consequential damages, incurred in connection with the use or performance of the product. This warranty shall be void if the product has been tampered with or improperly used. NEPTCO reserves the right to improve, enhance, and / or modify the features and specifications of these products.