

Royston® Roybond 750 Sprayable Primer

Roybond 750 is a solvent based, fast drying, single component, sprayable rubber resin primer to be used on properly prepared surfaces prior to the placement of Royston® preformed sheet membranes.

Roybond 750 adheres firmly to properly prepared concrete, wood, aged asphalt, metal or other common construction materials. It enables an effective and continuous bond to be formed between the substrate and the preformed Royston® rubberized asphalt sheet membrane. Roybond 750 is to be applied when ambient and substrate temperatures are 45°F and rising.

FEATURES	BENEFITS
Specially designed primer for Royston® sheet membranes	Generates high peel strength
Low Viscosity	Easily distributed
High yield	Cost effective
Sprayable	Rapid uniform application

USES

Application

- As a primer for the Royston® line of architectural, bridge and reflective cracking membranes.

Locations

- Bridges, Highways, & Tunnels
- Airport Runways / Taxiways
- Parking Structures
- Commercial Buildings & Other Below Grade Architectural Membrane Applications

Substrate

- Cured Concrete
- Steel
- Aged Asphalt
- Wood

SURFACE PREPARATION:

New Surfaces: Should be flat, clean, dry and free from dust, dirt, mud, oil, grease and other contaminants. Holes, voids and uneven surfaces with imperfections over ¼" peak to valley, should be prepared with suitable material to obtain a level substrate. Ensure that all sharp protrusions are removed prior to installation.

Existing Surface: Existing waterproofing must be removed in its entirety. Surface must be cleaned with high pressure water or other acceptable method and allowed to dry. Surface must be swept and blown clean prior to primer application.

MIXING:

Roybond 750 must be stirred well prior to use to ensure uniformity. A drill and spiral mixing paddle are strongly recommended.

APPLICATION:

Roybond 750 Primers should be stirred before using and applied at a rate of approximately 300 sq. ft. per gallon without dilution. The preferred method of application is by airless spray equipment. A plural component sprayer capable of metering products at up to a 30:1 ratio is recommended. The primer should be dry to the touch prior to the installation of the Royston® membrane system. Drying typically requires 20-30 minutes, but varies depending on temperature and humidity. Brush out any puddles of primer to allow for uniform drying. If the membrane has not been applied within 24 hours, re-coating of the substrate may be necessary due to dust accumulation. Roybond 750 is applied at ambient and substrate temperatures of 45°F and rising.

TECHNICAL DATA – FLAMMABLE LIQUID		
Properties:	Test Method	Typical Properties
Color:		Dark Red Oxide
Density, (lbs./gal.)		7.44 ± 0.1 lbs/gal
Viscosity	#2 Zahn Brookfield	28 – 54 seconds
Flash Point	Tag Close Cup	81 °F
% Solids (by weight)	Internal	17.46% ± 1% 1 hour @ 105°C

COVERAGE:

300 sq. ft./gallon when used as a primer for bridge and architectural membranes. Coverage will vary due to porosity of the substrate.

LIMITATIONS:

Do not apply membrane to wet primer.
Do not apply primer to foam substrates or forms.
Do not apply primer to asphalt less than 1 year old.

CAUTION:

Direct contact with skin should be avoided as it can cause skin irritation. Protective clothing, goggles and gloves are recommended. In case of direct contact with the skin, wash with soap and water. In case of accidental contact with eyes, flush immediately with plenty of water and report to a doctor. Fatal if taken internally. Keep away from open flame.

PROPER RESPIRATION EQUIPMENT REQUIRED**CLEAN UP:**

Use toluene

PACKAGING:

1 Gallon Units (4 per case)
5 Gallon Pails
55 Gallon Drums

SHELF LIFE:

1 Year

STORAGE CONDITIONS:

Materials must be kept in a dry area at temperatures between 50° F and 95° F (10° C - 35° C) in the original unopened containers during all phases of delivery, storage and handling.

Contact Chase Construction Products

Global Operations Center 295 University Avenue Westwood, MA 02090 USA www.chasecorp.com	Toll Free (US only): 800-323-4182 Tel: 781-332-0700 Fax: 781-332-0701 Email: info@chasecorp.com
---	--

Warranty & Limitation of Seller's Liability

The information contained herein is provided for product selection only, and is not to be considered as a specification or performance data. Chase Construction Products (a division of Chase Corporation) warrants the product for a period of one (1) year from the date of initial shipment to the initial purchaser, that the products meet the parameters listed on the applicable Technical Data Sheet. Chase makes no warranty of any kind, expressed or implied, including that of merchantability, other than that products conform to Chase's current quality control standards at time of manufacture. If breach of warranty is established, the buyer's exclusive remedy shall be repayment of purchase price of the non-conforming product to replace the non-conforming product. The buyer expressly waives any claim to additional damages, including without limitation, incidental or consequential damages. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale.