





PRODUCT

SF26 Urethane; Polyurethane: Solvent Free Waterbased Aliphatic Polyester Dispersion

DESCRIPTION

SF26 is a translucent aliphatic waterbased urethane resin that contains no solvent and has good physical properties without the use of cross linkers. SF26 is a single component that must be coalesced with solvents, resins or additives to form a good film. SF26 is an extremely hard resin and provides good chemical and abrasion resistance in formulated coatings.

BENEFITS

- Solvent free SF26 allows formulator latitude in choosing the correct co-solvent for the application
- Extremely low VOC coatings can be developed using SF26
- Coatings that need quick tack free properties can be formulated with SF26
- Imparts exceptional UV resistance.
- Imparts high chemical resistance with excellent abrasion resistance

APPLICATIONS

- Wood Coatings
- Concrete Coatings
- Metal Coatings
- Base Polymer for OEM Paints
- Exterior Paints

TECHNICAL INFORMATION

٠	% Solids	36-38%
٠	Viscosity, cps @ 25°C	25 - 500
٠	Specific Gravity	1.06 ± 0.01
٠	Wt./Gallon	8.75 lbs. ± 0.1
٠	рН	7.75 ± 0.75
٠	VOC (g/L)	< 50 g/L

TYPICAL PROPERTIES

•	Taber CS10 Wheel ¹	14 mg
•	Hardness (Sward, 1 week)	55
•	Tensile Strength ²	5500
•	Elongation ²	200%

TEST METHODS (ASTM Method)

% Solids - D-2369	Hardness - D-2134	Viscosity – D-2196				
Abrasion - D-4060	Appearance - E-284	pH- E-70				
Tensile - D-412	Elongation - D-412	VOC Properties - D-3960				
Weight/Gallon - D-1475						

Viscosity measured using a Brookfield LVF, #1 spindle ¹Taber Abrasion Weight Loss 1000 gram load/1000 cycles ²Instron tester; films pulled at 2 inches per minute

FORMULATING TIPS

SF26 does not film form at room temperature. SF26 may be further crosslinked with carbodimide or aziridine. SF26 is generally compatible with Chase QW resin series or a variety of acrylic resin emulsions.

STORAGE AND HANDLING

Store between 55 to 95°F. Consult Safety Data Sheet prior to working with the material.



PRODUCT INFORMATION

Product Name: SF26

CLEAN UP

Soap and water. All applicators and utensils must be thoroughly cleaned prior to use. For further information, refer to the Safety Data Sheet.

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contains Chase's limited warranty and other terms and conditions.

02/17