



CIM 800, 1000, OR 1061  
MINIMUM 60 MILS WET

HAIRLINE CRACKS  
NO TREATMENT NEEDED

SHRINKAGE CRACKS BETWEEN 1/16" AND 1/4" MUST BE  
STRIPE COATED WITH CIM 1000 TROWEL GRADE

- NOTES: 1. (OPTIONAL/NOT SHOWN) PRIME CONCRETE WITH CIM ECO OR CIM EMT EPOXY PRIMER.
2. CRACKS GREATER THAN 1/4" MUST BE ROUTED OUT AND TREATED LIKE A JOINT.

  	
TITLE	
CRACK TREATMENT DETAIL	
SIZE	DWG NO
	CIM-C0005
SCALE	SHEET
NONE	1 OF 1