

# Royston® 10AN EASY PAVE Bridge Deck Membrane

Royston® 10AN Easy Pave Bridge Deck Membrane is a prefabricated reinforced laminate consisting of a spun bonded polyester top surface, impregnated fiberglass, non-woven, inner mat sandwiched between layers of a polymer modified bitumen. A unique 3- inch leading edge guarantees a positive compound-to-compound seal at the overlap. Transverse seals are easily made using Royston® Flex-Flo Adhesive Sealant (FFAS), Royston® 104 Caulkable Mastic (104CM) or via heat sealing.

FEATURES	BENEFITS
3" Leading edge	Adhesive to adhesive bond creating a water-tight seam
Uniform thickness	Factory made sheet ensures consistent mil thickness
Flexible	Allows for minor amount of movement related to thermal expansion/contraction, settlement or shrinkage
Cold applied	Eliminates dangers of hot liquids
Spun-bonded top surface	Mechanical protection & increased adhesion to overlay

## USES

### Application

- Roadway/Bridge Deck Waterproofing Membrane

### Locations

- Bridges/Highways/Tunnels/Airport Runways
- Balconies
- Parking Garages

### Substrate

- Concrete
- Asphalt
- Steel
- Wood

PHYSICAL PROPERTIES		
Properties	Test Method	10AN EP Values
Wearing Surface		Asphalt, concrete, terrazzo, block
Color		Black with spun bonded polyester to surface
Top Surface		¼ mil mylar film
Thickness		60±5 mils
Weight		0.35 ± 0.05 lbs/ft <sup>2</sup>
Elongation Compound Only	ASTM D1000 Mod. <sup>1</sup>	1000% min.
Tensile Strength	ASTM D1000 Mod. <sup>1</sup>	833 psi min. (58.5 kg/cm <sup>2</sup> )
Permeance	ASTM E96 Method B	.05 u.s. perms max.
Compound Softening Point	ASTM D36	230° F min. (110° C)
Compound Penetration	ASTM D5	55±15 @ 77° F 5 sec 100 needle
Puncture Resistance	ASTM E154	40 lbs. min
Pliability	ASTM D146 <sup>4</sup>	No cracks or splits at 180° bend
Cycling Shear Strength	TWI100336 <sup>2</sup> .635 cm (.25") Recovery 0° C (32° F)	Constant load @ 1000 cycles, no damage
Resistance to Hydrostatic Head	RS100329 <sup>3</sup>	150 ft (45.75 m) min.
Water Absorption	ASTM D1228 – 72 hrs	.25% max
Peel Adhesion	180° peel after 1 hour primed steel	5 lb/in (0.892 kg/cm) min
Reinforcement		Non-woven fiberglass 48 g/m <sup>2</sup>

NOTES:

1. ASTM D1000 Method using CRE Tester with a 4" jaw separation at a speed of 10"/min. PSI calculated from #/in. width at specified thickness.
2. TWI 100336 uses membrane properly applied to two primed steel panels with a 1" gap between panels. At specified test temperature the gap is cycled to the specified opening for the specified no. of cycles. For Shear Strength, the force/unit of the first cycle is recorded. For Shear Stress recovery any damage after the no. of cycles to constant load and the no. of cycles required to reach constant load is noted.
3. RS 100329 hydrostatic head tests are performed on membrane properly applied to primed concrete. The surface is sealed with a pressure chamber and water is introduced under pressure equal to specified head.
4. 1" Mandrel @ -25° F (-31° C)

## WHAT IT DOES

Royston® 10AN Easy Pave Bridge Deck Membrane forms an impermeable barrier between the concrete decks and the surfacing material. It effectively prevents moisture, salts and deicing chemicals from infiltrating the underlying concrete surfaces, thus eliminating the damage to steel reinforcing and concrete damage caused by freeze-thaw cycles.

The spun bonded polyester top surface provides better traction during paving for rubber tired trucks, pavers and other vehicles. Although the spun polyester facing mat has a high melting point, the hot asphalt forms a strong bond to the bituminous compound during compaction.

## WHERE TO USE IT

Royston® 10AN Easy Pave Bridge Deck Membrane should be used to cover concrete decking of new highway bridges prior to the application of the surfacing material. It may also be used during resurfacing of old bridges to prevent further ingress of corrosive agents. Also, excellent for use on parking decks, balconies, plazas and other locations where waterproofing is required.

## SURFACE PREPARATION

New Surface: Ensure that surface is clean, dry and free of any dirt, dust, debris or other contaminant. Surface must be swept and blown clean prior to primer and membrane application.

Existing Surface: Profile should be milled using minimal tooth spacing (3/16" (4.75mm) or less). Ensure that the previous water proofing system has been completely removed. Grooves left in the concrete deck must be less than 3/16" (4.75mm). Surface must be swept and blown clean prior to primer and membrane application.

Milled Surface: If grooves in the concrete deck are ¼" (6.35mm) or greater tenting will occur. A scratch coat of asphalt must be applied prior to the primer and membrane installation. All unstable locations in the deck must be patched/repared prior to the application of the scratch coat. The asphalt scratch coat should be allowed to cool to ambient temperature (2-3 hours). Surface must be swept and blown clean prior to membrane application. No primer is required when applying membrane to freshly placed asphalt scratch course.

Existing Asphalt: If the membrane is being applied over the surface of existing asphalt that is less than one (1) year old, no primer is required. The existing asphalt surface must be clean prior to membrane installation. If the asphalt surface is greater than 1 year in age, use the appropriate primer.

## USE OF PRIMER

Reference the applicable Roybond Primer technical data sheet for application procedures and rates. Roybond Primers should be stirred before using and applied at a rate of approximately 200 sq. ft. per gallon (without dilution) by brush, squeegee, or short nap. The primer should be dry to the touch before application of the membrane. This will require 20 to 30 minutes depending on temperature and humidity. Brush out any puddles of primer to allow for uniform drying.

*Roybond 713A:* Standard Primer

*Roybond 713B:* Low V.O.C. Primer

*Roybond 740:* Low temperature primer for use between 25°F (-4°C) and 45°F (7°C)

*Roybond 750:* Spray-able version of the 713A standard primer

## APPLICATION

For best results, the membrane should be applied at surface and ambient temperatures of 25°F or higher. The membrane should be applied by hand rolling onto the application surface. The release film should be removed as the application proceeds. The membrane should be applied to the decking surface and terminated at the curb. If using Flex Flo Adhesive Sealant (FFAS), the membrane should be embedded in FFAS at all perimeter edges/termination points. A thin bead of FFAS or 104CM is to be applied on the surface of the membrane along all perimeter edges/termination points at the conclusion of the membrane installation.

Each roll should be applied to overlap the previous roll by a minimum of 3-6 inches. Overlapping of the membranes typically results in the loss of 10% of the usable surface area, reducing the coverage area from 200 ft<sup>2</sup> to 180 ft<sup>2</sup> per roll. The overlap at the edge is self-sealing due to the placement of the spun bonded polyester mat providing compound-to-compound contact. The transverse joint lap at the end of each roll should be sealed by heating with a propane torch to melt the spun bonded polyester mat and fuse the surfaces together. Patching may also be done by the heat sealing method or with the use of Royston® 104CM or Flex-Flo Adhesive Sealant.

Narrow strips (curb strips) are available for easy application to curb areas. If a curb strip is required by the specifying agency or engineer, the membrane should be brought up the curb to a point ½ inch below the top of the overlay, or as otherwise indicated by the engineer. Care should be taken to avoid rupture of the membrane when molding it to irregular contours.

Membrane should not be applied if weather will not permit for the paving of asphalt on top of the membrane prior to rain. If inclement weather occurs prior to paving and water is able to migrate under the membrane, the removal, drying of the deck and reinstallation of the membrane is required.

For additional instructions, reference the most current version of the "Royston® Waterproofing Membrane Installation Guidelines".

## APPLICATION OF HOT ASPHALT OVERLAY

The asphalt MUST be between 290°F and 340°F at the time of application. Rubber tired pavers and trucks may be driven on the membrane provided care is taken to prevent sudden starts, stops or turns. As the hot asphalt is compacted, it bonds firmly to the surface of the membrane. A minimum of 1 ½ inches (32mm) of compacted asphalt is required to ensure proper bond between overlay and substrate.

## AVAILABILITY

Rolls: 4' wide x 50' long (28 rolls per pallet)

**SHELF LIFE:** 1 year

## STORAGE CONDITIONS

Must be stored in a cool shaded area between 35°F and 90°F.

### **Contact Chase Construction Products**

**Global Operations Center**

295 University Avenue  
Westwood, MA 02090  
USA  
[www.chasecorp.com](http://www.chasecorp.com)

Toll Free (US only): 800-323-4182  
Tel: 781-332-0700  
Fax: 781-332-0701  
Email: [info@chasecorp.com](mailto:info@chasecorp.com)

**Warranty & Limitation of Seller's Liability**

The information contained herein is provided for product selection only, and is not to be considered as a specification or performance data. Chase Construction Products (a division of Chase Corporation) warrants the product for a period of one (1) year from the date of initial shipment to the initial purchaser, that the products meet the parameters listed on the applicable Technical Data Sheet. Chase makes no warranty of any kind, expressed or implied, including that of merchantability, other than that products conform to Chase's current quality control standards at time of manufacture. If breach of warranty is established, the buyer's exclusive remedy shall be repayment of purchase price of the non-conforming product to replace the non-conforming product. The buyer expressly waives any claim to additional damages, including without limitation, incidental or consequential damages. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale.