

Rosphalt® 50-LT

Rosphalt 50-LT is a patent pending concentrated thermoplastic polymeric asphalt additive supplied to batch or drum plants in a dry powder form. When added at forty five (45 lbs) pounds per ton of asphalt in a job mix formulation design with target air voids of 1% to 1.5%, Rosphalt 50-LT provides a waterproofing wear- course that is highly resistant to rutting and shoving and is also Fuel Resistant. Rosphalt 50-LT is produced at temperatures consistent with traditional hot mix asphalt.

Common applications are new and replacement overlays on composite, orthotropic steel, post tension box girder, steel grid, wood and other common bridge decking that require corrosion protection and a high performance, long lasting wearing course. Additional applications include enhanced road areas requiring high performance, rut and shove resistant pavements such as high traffic intersections, entrance and exit ramps, terminal turnarounds, toll booths, airports, ports & terminals and auto racetracks.

FEATURES	BENEFITS
Integrated waterproofing & wearing course	One step installation
Uses standard paving equipment	No special equipment required
Lifespan of 3.5 times asphalt	Reduced life cycle costs
Rapid return to service	Ideal for high traffic overhead structures
Dry mix additive	Easily purchased and transported in any quantity
Rut & Shove Resistant	Longer Lasting Pavement
Fuel Resistant	Tested to FAA P-401 spec

ADVANTAGES

Easy Installation: Use standard paving equipment and one-step integral waterproofing wearing course allows for rapid installation. Providing labor savings and quicker return to service when compared to competitive technology

Rapid Return to Service: Rosphalt is returned to service in as little as 1 hour (Pavement cools to 140°F (60°C))

Life Cycle Costs: Based on beam fatigue test data, Rosphalt 50 has a typical life span of 3.5 times traditional PG64-22 polymer modified asphalt concrete pavements. This 3.5 times life span reduces Rosphalt 50's life cycle costs, creating an advantage when compared to alternate technologies.

Rut & Shove Resistance: Based on independent lab testing performed by the Asphalt Institute and Worcester Polytechnic Institute, Rosphalt 50 exhibits almost 2/3 less rutting than PG64-22.

INDEPENDENT TEST DATA OF PG64-22 WITH ROSPHALT 50		
Properties	Test Method	Result
Color		Black
Shelf Life		1 Year
Performance Grade (Note 1) Table 3 will be provisional specification	AASHTO M320	Table 1 PG 94-34 Table 2 PG94-34 Table 3 PG70E-34 (E) Extreme
Elastic Recovery	ASTM D6084	92% @ 10°C
Hydraulic Conductivity*	ASTM D5084	Impermeable 10e ⁷ or higher
Permeability (In-Situ)**	ASTM C1202	454.5 to 517.5 coulombs
Chloride Penetration	AASHTO T260	.02%
Beam Fatigue	AASHTO M320	> 250,000 cycles

* Property values include AASHTO Standards. The -34C can be verified from mix testing in IDT (Indirect Tensile Test)

** Full reports listed as part of In-Situ Test Report

USES

Application

- Nosing material in expansion joints
- Rut & shove resistance pavement

Locations

- Bridge decks & Approaches
- Airport Runways / Taxiways (Fuel Resistant)
- Toll Booth Areas
- Parking Garages
- High Traffic Intersections
- Race Tracks (Fuel Resistant)

Substrate

- Concrete
- Asphalt
- Steel
- Composite
- Wood

LIMITATIONS

- Minimum installation surface and substrate temperature of 40°F (Radiant heaters on the pavers can be used to operate in lower temperatures. Contact Chase for additional information.)
- For additional product limitations, reference the most current addition “Rosphalt Guidelines.”

MANUFACTURING AND INSTALLATION INSTRUCTIONS

Rosphalt is blended in the batch or drum plant with the aggregate prior to the addition of the liquid asphalt binder. The liquid asphalt binder is added and the materials are mixed for a minimum of 70 seconds. Rosphalt is transported in tarped trucks.

Please see the “Rosphalt Guidelines” for detailed manufacturing, quality assurance and installation instructions.

ESTIMATING QUANTITY

Asphalt containing Rosphalt typically weights 150 lbs per cubic foot but varies per job mix formulation. This equates to approximately 25 lbs per square foot when compacted to a 2” depth resulting in a yield of 80 square feet per unit of Rosphalt.

AVAILABILITY

Kit Size 45 lbs (2 x 22.5 lbs polyethylene bags)

Super Sacks (approx. 40 units)

Bulk Tanker

Colors: Black

STORAGE

DO NOT ALLOW PRODUCT TO FREEZE. Store in a dry area at temperatures between 50°F and 95°F (10°C - 35°C) in the original unopened containers.

CAUTION

The data contained herein reflects internal testing conducted by the manufacturer and by third parties who are responsible for the accuracy of the information. This document is not to be construed as a specification or specific application process. Chase Corporation assumes no liability outside specific limits specified herein.

Contact Chase Construction Products

Global Operations Center

295 University Avenue
Westwood, MA 02090
USA
www.chasecorp.com

Toll Free (US only): 800-323-4182
Tel: 781-332-0700
Fax: 781-332-0701
Email: info@chasecorp.com

Warranty & Limitation of Seller's Liability

The information contained herein is provided for product selection only, and is not to be considered as a specification or performance data. Chase Construction Products (a division of Chase Corporation) warrants the product for a period of one (1) year from the date of initial shipment to the initial purchaser, that the products meet the parameters listed on the applicable Technical Data Sheet. Chase makes no warranty of any kind, expressed or implied, including that of merchantability, other than that products conform to Chase's current quality control standards at time of manufacture. If breach of warranty is established, the buyer's exclusive remedy shall be repayment of purchase price of the non-conforming product to replace the non-conforming product. The buyer expressly waives any claim to additional damages, including without limitation, incidental or consequential damages. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale.